

## Retarding and water reducing admixture

### Uses

To increase the workability and/or strength of concrete of a given cement content whilst increasing its initial and final setting time. To facilitate the production of high quality concrete of improved durability and water tightness.

### Advantages

- Set retardation allows extra placing time for larger pours.
- Increased workability facilitates placing and compaction.
- High strengths without increase in cement content or reduction in workability.
- Strength specifications and workability can be maintained with less cement.
- Set retardation controls stiffening time of concrete in hot weather.

### Standards compliance

Conplast R conforms with BS 5075 Part 1, ASTM C494 Type D and BSEN 934-2.

### Description

Conplast R a brown chloride free liquid is based on a hydroxycarboxylic acid derivative which instantly disperses in water.

Conplast R disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively. This effect can be used to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content.

The retarding properties of Conplast R can also be beneficial in concrete where high cement content or high temperatures are involved. Cold joints in continuous pours may be avoided and the use of lower cement contents will reduce heat of hydration.

Conplast R is particularly suitable for cohesive and cement rich mixes. For lean mixes which are prone to segregation Conplast RP264\*<sup>†</sup> may prove more suitable.

### Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

### Dosage

The optimum dosage of Conplast R to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is 0.3 to 0.6 litres/100 kg of cementitious material, including PFA, GGBFS or microsilica.

### Use at other dosages

Dosages outside the normal range quoted above can be used to meet particular mix requirements. Contact Fosroc for advice in these cases.

### Effects of overdosing

An overdose of double the intended amount Conplast R will result in a significant increase in retardation as compared to that normally obtained at the intended dosage. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased.

The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

### Properties

<b>Appearance</b>	: Brown liquid
<b>Specific gravity (BSEN 934-2)</b>	: 1.14 @ 22°C + 2°C
<b>Water soluble chloride (BSEN 934-2)</b>	: Nil
<b>Alkali content (BSEN 934-2)</b>	: Typically less than 30g. Na <sub>2</sub> O equivalent/litre of admixture

### Instructions for use

#### Retardation

The level of retardation obtained may be varied by altering the dosage of Conplast R used, this will also alter the level of water reduction obtained. Retardation is also affected by factors other than the admixture, depending on the mix details and conditions involved. Major factors include the following:

- a) Cement replacement materials and SRC cements will usually give greater levels of retardation than concrete mixes made with ordinary Portland cement at the same admixture dosage. Trials need to be conducted to establish the required dosage.

# Conplast R\*

- b) High temperatures will require increased dosages to obtain the same change in stiffening time compared to a control mix.
- c) Changes in cement content, source or chemistry may lead to variations in the retardation obtained. The amount of tri-calcium aluminate in the cement has been identified as being one of the main contributory factors in this respect, with a lower level leading to greater retardation.
- d) The use of a combination of admixtures in the same concrete mix and or cement replacements may alter the setting time. Trials should always be conducted to determine such setting times.

## Compatibility

Conplast R is compatible with other Fosroc admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be premixed together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by trial mixes.

Conplast R is suitable for use with all types of Portland cements and cement replacement materials such as PFA, GGBFS and microsilica.

## Dispensing

The correct quantity of Conplast R should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact Fosroc for advice regarding suitable equipment and its installation.

## Estimating – packaging

Conplast R is available in 210 litre drums and bulk supply. For larger users, storage tanks can be supplied.

## Storage

Conplast R has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact Fosroc for advice.

**Freezing point:** Approximately -4°C

## Precautions

### Health and safety

Conplast R does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - **do not** induce vomiting.

For further information consult the Material Safety Data Sheet available for this product.

### Fire

Conplast R is water based and non-flammable.

### Cleaning and disposal

Spillages of Conplast R should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

\* Denotes the trademark of Fosroc International Limited

† See separate data sheet



## Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service

### Head Office

**telephone:** (+9714) 2858606

**fax:** (+9714) 2859649

**email:** agf@fosroc.com

### Regional offices

Dubai, Al Gurg Fosroc  
Abu Dhabi, Al Gurg Fosroc  
Bahrain, YBA Kanoo  
Kuwait, Boodai  
Oman, Al Amana  
Qatar, Tadmur

**telephone:** 285 8787  
**telephone:** 673 1779  
**telephone:** 17735454  
**telephone:** 4817618  
**telephone:** 771 5080  
**telephone:** 413628

**fax:** 285 2023  
**fax:** 673 1449  
**fax:** 17732828  
**fax:** 4832124  
**fax:** 771 7554  
**fax:** 440812

**email:** dubai@fosroc.com  
**email:** abudhabi@fosroc.com  
**email:** bahrain@fosroc.com  
**email:** kuwait@fosroc.com  
**email:** oman@fosroc.com  
**email:** qatar@fosroc.com

Al Gurg Fosroc  
LLC

Post Box 657, Dubai  
United Arab Emirates

[www.fosroc.com](http://www.fosroc.com)



UAE/0276/01/D